



Paper Specification  
TS – 29.3.2016

# SORA matt 1.1

**SORA matt 1.1** is a woodfree 2 side matt coated bulky graphical paper.

| Parameter                            | Standard              | 60   | 65   | 70   | 80   | 90   | 100  | 115  | 135  | 150  | Tolerance |
|--------------------------------------|-----------------------|------|------|------|------|------|------|------|------|------|-----------|
| Grammage<br>[g/m <sup>2</sup> ]      | ISO 536               | 60   | 65   | 70   | 80   | 90   | 100  | 115  | 135  | 150  | ± 2       |
| Spec. volume<br>[cm <sup>3</sup> /g] | ISO 534               | 1.05 | 1.06 | 1.06 | 1.07 | 1.07 | 1.08 | 1.08 | 1.10 | 1.10 | ± 0.04    |
| Smoot. Bendtsen<br>[ml/min]          | ISO 8791- 2           | 120  | 120  | 120  | 120  | 120  | 120  | 120  | 150  | 150  | ± 35      |
| Rel. humidity<br>[%]                 | DIN 19306             | 47.5 | 47.5 | 47.5 | 47.5 | 47.5 | 47.5 | 47.5 | 47.5 | 47.5 | ± 7.5     |
| Brightness<br>[%]                    | ISO 2470<br>(D65/10°) | 97   | 97   | 97   | 97   | 97   | 97   | 97   | 97   | 97   | ± 2       |
| Opacity<br>[%]                       | ISO 2471              | 86   | 87   | 89   | 92   | 94   | 96   | 97   | 98   | 98   | ± 2       |

*Given values can be used as guide values only and can be changed without prior notice.  
For a valid specification, please refer to the one most recently published on the website [www.goricane.si](http://www.goricane.si).  
Information on the supplies of FSC and PEFC certified products are available in the Sales department.*

